

## Review: Green Synthesis of Silver and Gold Nanoparticles

*Varahalarao Vadlapudi and D.S.V.G.K.Kaladhar*

<sup>1</sup>Department of Biochemistry, Dr Lankapalli Bullayya P G College,  
Visakhapatnam-530013, AP, India

<sup>2</sup>Department of Bioinformatics, GIS, GITAM University,  
Visakhapatnam-530045, AP, India

---

**Abstract:** Nanotechnology is a field that is mushrooming, making an impact in all spheres of human life. Nanobiotechnology represents an economic alternative for chemical and physical methods of nanoparticles formation. Presently available literature revealed that the NP synthesis using marine plants, microorganisms and algae as source has been unexplored and underexploited. The development of green processes for the synthesis of NP is evolving into an important branch of nanotechnology. It has many advantages such as, ease with which the process can be scaled up, economic viability, etc. Presently, the researchers are looking into the development of cost-effective procedures for producing reproducible, stable and biocompatible AgNPs and AuNPs. Antibiotic resistance is the world's major public healthcare problem. AgNPs and AuNPs particles play a vital role in nanobiotechnology as biomedicine against Drug-resistant bacteria.

**Key words:** Nanotechnology • Nanoparticles • Biomedicine

---

### INTRODUCTION

The word “nano” is used to indicate one billionth of a meter or  $10^{-9}$ . Nanoparticles are clusters of atoms in the size range of 1–100 nm. “Nano” is a Greek word synonymous to dwarf meaning extremely small. Nanotechnology is a field that is mushrooming, making an impact in all spheres of human life. Nanobiotechnology represents an economic alternative for chemical and physical methods of nanoparticles formation. Nanoparticles (NP) attract greater attention due to their various applications in different fields including “nanomedicine”. The term Nanotechnology was coined by Professor Norio Taniguchi of Tokyo Science University in the year 1974. Nanoparticles can be broadly grouped into two, namely, organic nanoparticles which include carbon nanoparticles (fullerene) while, some of the inorganic nanoparticles include magnetic nanoparticles, noble metal nanoparticles (like gold and silver) and semi-conductor nanoparticles (like titanium oxide and zinc oxide). There is a growing interest in inorganic nanoparticles i.e. of noble metal nanoparticles (Gold and silver) as they provide superior material properties with functional versatility. Metallic nanoparticles are most

promising and remarkable biomedical agents. Silver, Aluminum, Gold, Zinc, Carbon, Titanium, Palladium, Iron, Fullerenes and Copper have been routinely used for the synthesis of nanoparticles. The use of AuNPs dates back to the 16th century, for both medical and staining purposes. There is a growing need to develop environmentally friendly processes through green synthesis and other biological approaches.

**Importance of the Study:** Presently available literature revealed that the NP synthesis using marine plant, microorganisms and algae as source has been unexplored and underexploited. Resistance to antimicrobial agents by pathogenic bacteria has emerged in recent years and is a major health problem. Seaweeds or benthic marine algae are the group of plants that live either in marine or brackish water environment. The use of marine algae in the synthesis of AuNPs emerges as an ecofriendly and exciting approach. Utilizing a biological source gives an easy approach, easy multiplication and easy increase of biomass and size uniformity. Antibiotic resistance is the world's major public healthcare problem. Combating the Drug-resistant bacteria is another important challenge. People who become infected with drug-resistant

microorganisms usually spend more time in the hospital and require a form of treatment that uses two or three different antibiotics and is less effective, more toxic and more expensive [1]. The development of green processes for the synthesis of NP is evolving into an important branch of nanotechnology [2, 3]. Plants have evolved in the presence of natural Nanomaterials. However, the probability of plant exposure to Nanomaterials has increased to a greater extent with the ongoing increasing production and use of engineered nano materials in a variety of instruments and goods. Plant mediated synthesis of metal nanoparticles is gaining more importance owing to its simplicity, rapid rate of synthesis of NP of attractive and diverse morphologies and elimination of elaborate maintenance of cell cultures and eco-friendliness. The reason for selecting plant for Biosynthesis is because they contain reducing agents such as Citric acid, Ascorbic acids, flavonoids, reductases and dehydrogenases and extracellular electron shuttlers that may play an important role in biosynthesis of metal nano particles [4].

**Significance of AgNPs:** It has been positioned as the 47<sup>th</sup> element in the periodic table, having an atomic weight of 107.8 and two natural isotopes 106.90 Ag and 108.90 Ag with abundance of 52 and 48% where as the Colloidal silver is of particular interest because of distinctive properties such as good conductivity, chemical stability, catalytic and antibacterial activity [5]. The medicinal and preservative properties of silver have been known for over 2,000 years. Silver is one of the basic element that makes up our planet. It is a rare, but naturally occurring element, slightly harder than gold and very ductile and malleable. AgNPs of many different shapes (spherical, rod-shaped, truncated, triangular nanoplates) were developed by various synthetic routes. Truncated triangular silver nanoplates were found to show the strongest anti-bacterial activity. The AgNPs have excellent antimicrobial property compared to other salts due to their extremely large surface area, which provides better contact with microorganisms. Silver ions and nanoparticles are highly toxic and hazardous to microorganisms. AgNPs have many applications; for example, they might be used as spectrally selective coatings for solar energy absorption and intercalation material for electrical batteries, as optical receptors, as catalysts in chemical reactions, for biolabelling and as antimicrobials. [6-8]. Synthesis of AgNPs using plant [9-13] fungal [14], Bacteria extracts [15] Antimicrobial and cytotoxic effects of AgNPs. Current research in inorganic

nanomaterials having good antimicrobial properties has opened a new era in pharmaceutical and medical industries. Silver is the metal of choice as they hold the promise to kill microbes effectively. AgNPs have been recently known to be a promising antimicrobial agent that acts on a broad range of target sites both extracellularly as well as intra-cellularly. The resistance conferred by bacteria to silver is determined by the 'sil' gene in plasmids [16]. AgNPs have exhibited antimicrobial effect on *Staphylococcus aureus* and *E. coli* [17]. NP take advantages of the oligodynamic effect that silver has on microbes [18]. Green Synthesis of Small AgNPs Using Geraniol and Its Cytotoxicity against cancer cell line Fibrosarcoma-Wehi 164 [19]. Whereas the cell proliferation was evaluated by a modified Crystal Violet colorimetric assay [20]. Green synthesis, antimicrobial and cytotoxic effects of AgNPs using *Eucalyptus chapmaniana* leaves extract [21]. Antimicrobial activities of AgNPs already done [22, 23]. Several scientists reported green synthesis of AgNPs using plant extracts such as *Jatropha curcas seeds* [24], *Acalypha indica leaf* [25], *banana peel* [26], *Chenopodium album leaf* [27], *Rosarugosa* [28], *Trianthema decandra roots* [29], *Ocimumsanctum stems and roots* [30], *Sesuvium portulacastrumleaves* [31], *Murraya koenigii (curry) leaf* [32], *Macrotyloma uniflorum seeds* [33], *Ocimum sanctum(Tulsi) leaf* [34], *Garcinia mangostana (mangosteen) leaf* [35], *Stevia rebaudiana leaves* [36], *Nicotiana tobaccumleaf* [37], *Ocimum tenuiflorum, Solanum trilobatum, Syzygium cumini, Centella asiatica and Citrus sinensisleaves* [38], *Arbutus unedo leaf* [39], *Ficus benghalensisleaf* [40], *mulberry leaves* [41] and *Olea europaea leaves* [42]. Currently AgNPs are widely used as antibacterial and antifungal agents in a diverse range of consumer products: air sanitizer sprays, detergents, soaps, shampoos, toothpastes and washing machine [43]. In the Synthesis of AgNPs carob leaf extract shown better speed in compared with other extracts [44]. The synthesis of stable AgNPs by the bioreduction method was investigated. Aqueous extracts of the manna of hedysarum plant and the soap-root (*Acanthe phylum bracteatum*) plant were used as reducing and stabilizing agents [45]. Preparation of nanoscaled gold materials has become very important due to their unique properties, which are different from those of the bulk materials [46].

**Significance of AuNPs Particles:** Gold is a well known biocompatible metal and colloidal gold was used as a drinkable solution that exerted curative properties for several diseases in ancient times [47]. AuNPs have a great

bactericidal effect on a several range of microorganisms; its bactericidal effect depends on the size and shape of the particle [48]. Recently there are a few, reports that algae is being used as a biofactory for synthesis of metallic nanoparticles [49]. AuNPs have wide range of applications in nano-scale devices and technologies due to its chemical inertness and resistance to surface oxidation [50]. AuNPs play a vital role in nanobiotechnology as biomedicine because of convenient surface bioconjugation with biomolecular probes and remarkable plasmon-resonant optical properties [51-53]. Many research articles reported the synthesis of AuNPs using plant extracts such as *Ficus religiosa* [54] *Memecylon umbellatum* [55], *Macrotyloma uniflorum* [56], *Brevibacterium casei* [57, 58], *Citrus limon*, *Citrus reticulata* and *Citrus sinensis* [59], *Piper pedicellatum* [60], *Terminalia chebula* [61], *Memecylon edule* [62], *Nyctanthes arbortristis* [63], *Murraya Koenigii* [64], *Mangifera indica* [65], *Banana peel* [66], *Cinnamomum zeylanicum* [67], *Cochlospermum gossypium* [68], *Euphorbia hirta* [69]. AuNPs have an important function in the delivery of nucleic acids, proteins, gene therapy, *in vivo* delivery, targeting, etc [70]. In the recent decade, gold nanoparticles (NPs) [71] have attracted significant interest as a novel platform for various applications such as nanobiotechnology and biomedicine. Nano size gold, an emerging nanomedicine is renewed for its promising therapeutic possibility high surface reactivity, resistance to oxidation and plasmon resonance [72]. Biogenic gold nanotriangles and spherical AgNPs were synthesized by a simple procedure using *Aloe vera* leaf extract as the reducing agent. The kinetics of gold nanotriangle formation was followed by UV-vis-NIR absorption spectroscopy and transmission electron microscopy (TEM) [73]. GGFE can provide an environmentally benign rapid route for synthesis of AuNPs that can be applied for various purposes. Biogenic AuNPs synthesized using GGFE exhibited excellent chemocatalytic potential [74].

**Activities of AuNPs:** The results showed that the leaf extract of menthol is very good bioreductant for the synthesis of AgNPs and AuNPs and synthesized NP active against clinically isolated human pathogens, *Staphylococcus aureus* and *E. coli*. [75]. The antibacterial efficacy of AuNPs increases because of their larger total surface area per unit [76]. AuNPs have antibacterial [77], [78]. The ability of AgNPs to release silver ions is a key to their bactericidal activity [79]. Ionic forms of gold shown to have cytotoxicity on various cell types and adverse

effects on red blood cells [80]. The study was conducted to prepare ~20 nm AuNPs by a chemical reduction method and evaluate their cytotoxicity by MTT assay using human dermal fibroblasts–fetal (HDF-f) [81], The toxicity of starch-coated AgNPs was studied using normal human lung fibroblast cells (IMR-90) and human glioblastoma cells (U251). The toxicity was evaluated using changes in cell morphology, cell viability, metabolic activity and oxidative stress [82]. Biosynthesis of AuNPs by using the leaf extract of *Saururus chinensis*, Bioreduction of gold ions by *S. chinensis* leaf extract resulted in the synthesis of cubic, truncated triangle and irregular structured nanoparticles were found toxic against *S. aureus*, *S. subtilis*, *E. coli*, *C. albicans* and *S. cerevisiae* both in liquid and solid group media [83]. AuNPs important activities like anticoagulant activity [84], anticancer [85], [86].

**Factors Affecting Biosynthesis of Nanoparticles:** Both AgNPs and AuNPs can be successfully synthesized by traditionally chemical and physical methods. However, these methods strongly depend on severe reaction conditions, for example, aggressive agents like sodium borohydride, hydrazinium hydroxide, cetyltriethylammonium bromide and harmful solvent system to environment and ecology, higher temperature and higher pressure have been used. Temperature plays an important role to control the aspect ratio and relative amounts of gold nanotriangles and spherical nanoparticles. Temperature variations in reaction conditions results in fine tuning of the shape, size and optical properties of the anisotropic nanoparticles [87]. The size of AuNPs was shown to increase at higher reaction temperatures as explained by an increase in fusion efficiency of micelles which dissipates supersaturation [88]. pH of the medium influence the size of nanoparticles at great concern. Other than pH and temperature other factors also play role in NP synthesis. The sizes of AuNPs decreases with increasing NaCl concentrations (size ranges, 5-16 nm) than those synthesized without addition of NaCl (size ranges 11-32 nm) [89].

**Synthesis and Characterization of AuNPs:** An aqueous chloroauric acid solution (10<sup>-3</sup> M) was added separately to the reaction vessels containing the ethanol extract of black tea and its tannin free fraction (10% v/v) and the resulting mixture was allowed to stand for 15 min at room temperature. Chloroauric acid was purchased from Merck, Darmstadt, Germany. The ethanol solution (10% v/v) was used as a negative control. The reduction of the Au<sup>3+</sup>

ions by these ethanol extracts in the solutions was monitored by sampling the aqueous component (2 ml) and measuring the UV-visible spectrum of the solutions. All samples were diluted three times with distilled water and the UV-visible spectra of these samples were measured on a Labomed Model UVD-2950 UV-VIS Double Beam PC Scanning spectrophotometer, operated at a resolution of 2 nm. Furthermore, AuNPs were characterized by transmission electron microscopy (model EM 208 Philips) [90].

**B.**In the synthesis of AuNPs, 10 ml of the aqueous extract of *Gracilaria corticata* was added to 90 ml of 10<sup>-3</sup> M aqueous HAuCl<sub>4</sub> solution in 500ml Erlenmeyer flask and stirred for 4 hr at 120 rpm at 40°C. Suitable controls were maintained throughout the conduct of experiments [91].

**Synthesis of AgNPs:** In a typical reaction procedure, 5 ml of plant extract was added to 100 ml of 1 × 10<sup>-3</sup> M aqueous AgNO<sub>3</sub> solution, with stirring magnetically at room temperature. The yellow color of the mixture of silver nitrate and plant extract at 0 min of reaction time changed very fast at room temperature after 2 min to a black suspended mixture. The concentrations of AgNO<sub>3</sub> solution and leaf extract were also varied at 1 to 4 mM and 5% to 10% by volume, respectively. UV visible (UV-vis) spectra showed strong surface Plasmon resonance (SPR) band at 420 nm and thus indicating the formation of AgNPs. The AgNPs obtained by plant extract were centrifuged at 15,000 rpm for 5 min and subsequently dispersed in sterile distilled water to get rid of any uncoordinated biological materials [92].

**Application:** The use of nanoparticles for biomedical applications, such as drug and gene delivery, biosensors, cancer treatment and diagnostic tools, has been extensively studied throughout the past decade [93-103]. Very recently, nanoparticles have gained significance in the field of Biomedicine. Plants and plant extracts can be effectively used in the synthesis of gold and AgNPs as a greener route. Shape and size control of nanoparticles is easily understood with the use of plants. The nanoparticles extracted from plants are used in many applications for benefit of humans.

## CONCLUSION

The “green” route for nanoparticle (NP) synthesis is of great interest due to eco-friendliness, economic prospects and feasibility and wide range of applications in nanomedicine, catalysis medicine, nano-optoelectronics, etc. It is a new and emerging area of

research in the scientific world, where day-by-day developments is noted in warranting a bright future for this field. This green chemistry approach toward the synthesis of AgNPs and AuNPs have many advantages such as, ease with which the process can be scaled up, economic viability, etc. It was concluded that plant mediated synthesis of AgNPs possess potential antimicrobial, anticoagulant activity, anticancer activities. The characterization analysis proved that the particle so produced in nano dimensions would be equally effective as that of antibiotics and other drugs in pharmaceutical applications. The use of AgNPs and AuNPs in drug delivery systems might be the future thrust in the field of medicine. The Green chemistry synthetic route can be employed for both silver and gold silver nanoparticles synthesis. Among the AgNPs, the biological organisms such as bacteria, fungi and yeast or several plant biomass or plant extracts have been used for nanoparticles synthesis used for a number of applications from electronics and catalysis to biology. The on-going research efforts are focussed on evaluating the safety of nanomedicine and formulating the international regulatory guidelines for the same, which is critical for further technology advancement. With vast technology push, there are many challenges head that need to be understood and solve in order to make the NP-based products commercially-viable. Presently, the researchers are looking into the development of cost-effective procedures for producing reproducible, stable and biocompatible AgNPs and AuNPs from bioresources.

## REFERENCES

1. Sun, Y.G. and Y.N. Xia, 2002. Shape-controlled synthesis of gold and silver nanoparticles. *Science*, 298: 2176-2179.
2. Raveendran, P., J. Fu and S.L. Wallen, 2006. A simple and green method for the synthesis of Au, Ag and Au-Ag alloy nanoparticles. *Green Chem.*, 8: 34-38.
3. Armendariz, V., J.L. Gardea-Torresdey, M. Jose Yacamán, J. Gonzalez, I. Herrera and J.G. Parsons, 2002. Gold nanoparticle formation by oat and wheat biomasses, *Proceedings of Conference on Application of Waste Remediation Technologies to Agricultural Contamination of Water Resources Kansas City, Mo, USA*.
4. Sunil Pandey, Goldie Oza, Ashmi Mewada and Madhuri Sharon, 2012. Green Synthesis of Highly Stable Gold Nanoparticles using, *Momordica charantia* as Nano fabricator. *Archives of Applied Science Research*, 4(2): 1135-1141.

5. Frattini, A., N. Pellegri, D. Nicastro and O. De Sanctis, 2005. Effect of amine groups in the synthesis of Ag nanoparticles using aminosilanes. *Mat Chem Phys.*, 94: 148.
6. Magudapathy, P., P. Gangopadhyay, B.K. Panigrahi, K.G.M. Nair and S. Dhara, 2001. Electrical transport studies of Ag nanoclusters embedded in glass matrix. *Physica B.*, 299(1-2): 142-146.
7. Joerger, R., T. Klaus and C.G. Granqvist, 2000. Biologically produced silver-carbon composite materials for optically functional thin-film coatings. *Adv Mater.*, 12(6): 407-409.
8. Panacek, A., L. Kvitek, R. Prucek, M. Kolar, R. Vecerova, N. Pizurova, *et al*, 2006. Silver colloid nanoparticles: Synthesis, characterization and their antibacterial activity. *J. Phys. Chem B.*, 110(33): 16248-16253.
9. Khan, M., M. Khan, S.F. Adil, M.N. Tahir, W. Tremel, H.Z. Alkhatlan, A. Al-Warthan and M.R. Siddiqui, 2013. Green synthesis of silver nanoparticles mediated by *Pulicaria glutinosa* extract. *Int. J. Nanomedicine.*, 8: 1507-16.
10. Shankar, S.S., A. Ahmad and M. Sastry, 2013. Geranium leaf assisted biosynthesis of silver nanoparticles. *Bio-technol Prog.*, 19(6): 1627-1631.
11. Sivakumar, J., C. Premkumar, P. Santhanam and N. Saraswathi, 2011. Biosynthesis of Silver Nanoparticles Using *Calotropis gigantea* Leaf. *African Journal of Basic & Applied Sciences.*, 3(6): 265-270.
12. Song, J.Y. and B.S. Kim, 2009. Rapid biological synthesis of silver nanoparticles using plant leaf extracts. *Bioprocess Biosyst. Eng.*, 32: 79-84.
13. Akl M. Awwad., Nida M. Salem and Amany O. Abdeen, 2013. Biosynthesis of silver nanoparticles using Loquat leaf extract and its antibacterial activity. *Adv. Mat. Lett.*, 4(5): 338-342.
14. Absar, Ahmad., Priyabrata Mukherjee, Satyajyoti Senapati, Deendayal Mandal, M. Islam Khan, Rajiv Kumar and Murali Sastry, 2003. Extracellular biosynthesis of silver nanoparticles using the fungus *Fusarium oxysporum*. *Colloids and Surfaces B: Biointerfaces.*, 28(4): 313-318.
15. Silambarasan, S. and Abraham Jayanthi, 2013. Biosynthesis of silver nanoparticles using *Pseudomonas fluorescens*. *Research, Journal of Biotechnology*, 8(3):
16. Silver, S., 2003. Bacterial silver resistance, molecular biology and uses and misuses of silver compounds, *Fems Microbiol Rev.*, 27(2-3): 341.
17. Shahverdi, A.R., A. Fakhimi, H.R. Shahverdi and S. Minaian., 2007. Synthesis and effect of silver nanoparticles on the antibacterial activity of different antibiotics against *Staphylococcus aureus* and *Escherichia coli*. *Nanomed.*, 3: 168.
18. Prabu, N., T. Divya Raj, K. Yamuna Gowri, S. Ayisha Siddiqua and Joseph Pushpa, 2010. *Innocent D. Digest Journal of Nanomaterials and Biostructures.*, 5(1): 185-189.
19. Mona Safaepour, Ahmad Reza Shahverdi, Hamid Reza Shahverdi, Mohammad Reza Khorramizadeh and Ahmad Reza Gohari, 2009. Green Synthesis of Small Silver Nanoparticles Using Geraniol and Its Cytotoxicity against Fibrosarcoma-Wehi 164. *Avicenna J. Med. Biotechnol.*, 1(2): 111-115.
20. Saadat, F., K. Zomorodian, M.M. Pezeshki and M.R. Khorramizadeh, 2003. The potential role of non-steroidal anti-inflammatory drugs, Nsaids in chemoprevention of cancer. *Pak J. Med. Sci.*, 19(3): 13-17.
21. Ghassan Mohammad Sulaiman, Wasnaa Hatif Mohammed, Thorria Radam Marzoog, Ahmed Abdul Amir Al-Amiery, Abdul Amir H. Kadhum and Abu Bakar Mohamad, 2013. Green synthesis, antimicrobial and cytotoxic effects of silver nanoparticles using *Eucalyptus chapmaniana* leaves extract, *Asian Pac J. Trop Biomed.*, 3(1): 58-63.
22. Krishnaraj, C., E.G. Jagan, S. Rajasekar, P. Selvakumar, P.T. Kalaichelvan and N. Mohan, 2010. Synthesis of silver nanoparticles using *Acalypha indica* leaf extracts and its antibacterial activity against water borne pathogens. *Colloids and Surfaces B: Biointerfaces.*, 76: 50-56.
23. Tripathi, A., N. Chandrasekaran, A.M. Raichur and A. Mukherjee, 2009. Antibacterial application of silver nanoparticles synthesized by aqueous extract of *Azadirachta indica*, *Neem* leaves. *J. Biomedical Nanotechnol.*, 5: 93-98.
24. Bar, H., D.K. Bhui, S.P. Gobinda, P.M. Sarkar, S. Pyne and A. Misra, 2009. Green synthesis of silver nanoparticles using seed extract of *Jatropha curcas*. *Physicochem Eng Aspects.*, 348: 212-216.
25. Krishnaraj, C., E.G. Jagan E.G.S. Rajasekar, P. Selvakumar, P.T. Kalaichelvan and N. Mohan, 2010. Synthesis of silver nanoparticles using *Acalypha indica* leaf extracts and its antimicrobial activity against water borne pathogens. *Colloids Surf B Biointerfaces.*, 76: 50-56.

26. Bankar, A., B.B. Joshi, A.R. Kumar and S. Zinjarde, 2009. Banana peel extract mediated novel route for synthesis of silver nanoparticles. *Colloid Surf A Physicochem Eng Aspect.*, 368: 58-63.
27. Dwivedi, A.D. and K. Gopal, 2010. Biosynthesis of silver and gold nanoparticles using *Chenopodium album* leaf extract, *Colloid Surf A Physicochem Eng. Aspect.*, 369: 27-33.
28. Dubey, S.P., M. Lahtinen and M. Sillanpaa, 2010. Green synthesis and characterization of silver and gold nanoparticles using leaf extract of *Rosarugosa*. *Colloid Surf A Physicochem Eng. Aspect.*, 364: 34-41.
29. Geethalakshmi, E. and D.V. Sarada, 2010. Synthesis of plant-mediated silver nanoparticles using *Trianthema decandra* extract and evaluation of their antimicrobial activities. *Int. J. Eng. Sci. Tech.*, 2: 970-975.
30. Ahmad, N., S. Sharma, M.K. Alam, V.N. Singh, S.F. Shamsi, B.R. Mehta and A. Fatma, 2010. Rapid synthesis of silver nanoparticles using dried medicinal plant of basil. *Colloids Surf B Biointerfaces.*, 81(1): 81-86.
31. Nabikhan, A., K. Kandasamy, A. Raj and N.M. Alikunhi, 2010. Synthesis of antimicrobial silver nanoparticles by callus and leaf extracts from saltmarsh plant, *Sesuvium portulacastrum* L. *Colloids Surf B Biointerfaces.*, 79: 488-493.
32. Christensen, L., S. Vivekanandhan, M. Misra and A.K. Mohanty, 2011. Biosynthesis of silver nanoparticles using *Murraya koenigii* curry leaf an investigation on the effect of broth concentration in reduction mechanism and particle size. *Adv. Mater Letters.*, 2: 429-434.
33. Vidhu, V.K., A. Aromal and D. Philip, 2011. Green synthesis of silver nanoparticles using *Macrotyloma uniflorum*. *Spectrochim Acta A Mol Biomol Spectros.*, 83: 392-397.
34. Singhal, G., R. Bhavesh, K. Kasariya, A.R. Sharma and R.P. Singh, 2011. Biosynthesis of silver nanoparticles using *Ocimum sanctum*, Tulsi leaf extract and screening its antimicrobial activity, *J. Nanopart Res.*, 13: 2981-2988.
35. Veerasamy, R., T.Z. Xin, S. Gunasagan, T.F. Xiang, E.F. Yang, N. Jeyakumar and S.A. Dhanaraj, 2011. Biosynthesis of silver nanoparticles using mangosteen leaf extract and evaluation of their antimicrobial activities, *J. Saudi Chemical Society.*, 15: 113-120.
36. Yilmaz, M., H. Turkdemir, M.A. Kilic, E. Bayram, A. Cicek, A. Mete and B. Ulug, 2011. Biosynthesis of silver nanoparticles using leaves of *Stevia rebaudiana*. *Mater Chem Phys.*, 130: 1195-1202.
37. Parasad, K.S., D. Pathak, A. Patel, P. Dalwadi, R. Prasad, P. Patel and K. Selvaraj, 2011. Biogenic synthesis of silver nanoparticles using *Nicotiana tobaccum* leaf extract and study of their antimicrobial effect. *Afr J. Biotechnol.*, 10(8): 122-130.
38. Logeswari, P., S. Silambarasan and J. Abraham, 2012. Synthesis of silver nanoparticles using plants extract and analysis of their antimicrobial property, *J. Saudi Chem Soc.*, doi:10.1016/j.jscs.04.007
39. Kouvaris, P., A. Delimitis, V. Zaspalis, D. Papadopoulos, S.A. Tsiapas and N. Michalidis, 2012. Green synthesis and characterization of silver nanoparticles produced using *Arbutus Unedo* leaf extract. *Mater Letters*, 76: 18-20.
40. Saxena, A., R.M. Tripathi, F. Zafar and P. Singh, 2012. Green synthesis of silver nanoparticles using aqueous solution of *Ficus benghalensis* leaf extract and characterization of their antimicrobial activity. *Mater Letters*, 67: 91-94.
41. Awwad, A.M. and N.M. Salem, 2012. Green synthesis of silver nanoparticles by mulberry leaves extract, *Nanosci Nanotechnol.*, 2: 125-128.
42. Awwad, A.M., N.M. Salem and A. Abdeen, 2012. Biosynthesis of silver nanoparticles using *Olea europaea* leaves extract and its antibacterial activity, *Nanosci Nanotechnol.*, 2: 164-170.
43. Buzea, C., *et al.*, 2007. Nanomaterials and nanoparticles sources and toxicity. *Biointerphases*, 2(4): 17-71.
44. Akl, M. Awwad, N. M. Salem and Amany O. Abdeen, 2013. Green synthesis of silver nanoparticles using carob leaf extract and its antibacterial activity. *International Journal of Industrial Chemistry.*, 4: 29.
45. Mehrdad, Forough. and Khalil Farhadi, 2010. Biological and green synthesis of silver nanoparticles, *Turkish J. Eng. Env. Sci.*, 34: 281-287.
46. Armendariz, V., 2004. Size controlled gold nanoparticle formation by *Avena sativa* biomass, *Journal of Nanoparticle Research.*, 6: 377-382.
47. Daniel, M.C. and D. Astruc, 2004. Gold nanoparticles assembly, supramolecular chemistry, quantum-size-related properties and applications toward biology, catalysis and nanotechnology. *J. Chem., Rev.*, 104: 293-346.
48. Dror-Ehre, A., H. Mamane, T. Belenkova, G. Markovich and A. Adin, 2009. Silver nanoparticle - *E coli* colloidal interaction in water and effect on *E coli* survival. *J. Colloid Interface Sci.*, 339: 521-526.

49. Almeida, C.L.F., S. De, H. Falcao, D. De, G.R. Lima, A. De *et al*, 2011. Bioactivities from marine algae of the Genus *Gracilaria*. *Int. J. Mol. Sci.*, 12: 4550-4573.
50. Sugunan, A., C. Thanachayanont, J. Dutta and J.G. Hilborn, 2005. Heavy-metal ion sensors using chitosan-capped gold nanoparticles. *Adv. Mater.*, 6: 335-340.
51. Daniel, M.C. and D. Astruc, 2004. Gold nanoparticles assembly, supramolecular chemistry, quantum-size-related properties and applications toward biology, catalysis and nanotechnology. *Chem. Rev.*, 104: 293-346.
52. Wu, C.C. and D.H. Chen, 2010. Facile green synthesis of gold nanoparticles with gum arabic as a stabilizing agent and reducing agent. *Gold Bull.*, 43: 234-239.
53. Kreibitz, U. and M. Vollmer, 1995. Optical properties of metal clusters. Berlin, Springer-Verlag.
54. Kirtee, Wani, Amit Choudhari Rajeev Chikate and Ruchika Kaul-Ghanekar, 2013. Synthesis and characterization of gold nanoparticles using *Ficus religiosa* extract. *Carbon - Sci. Tech.*, 5(1): 203-210.
55. Arunachalam, K.D., S.K. Annamalai and S. Hari, 2013. One-step green synthesis and characterization of leaf extract-mediated biocompatible silver and gold nanoparticles from *Memecylon umbellatum*. *Int J. Nanomedicine*, 8: 307-1315.
56. Aromal, S.A., V.K. Vidhu and D. Philip, 2012. Green synthesis of well-dispersed gold nanoparticles using *Macrotyloma uniflorum*. *Spectrochim Acta A Mol. Biomol Spectrosc.*, 85(1): 99-104.
57. Kalishwaralal, K., V.V. Deepak, S. Ram Kumar Pandian, M. Kottaisamy, S. Barathmani Kanth, B. Kartikeyan and S. Gurunathan, 2010. Biosynthesis of silver and gold nanoparticles using *Brevibacterium casei*. *Colloids Surf B Biointerfaces.*, 1;77(2): 257-262.
58. Mittal, A.K., Y. Chisti and U.C. Banerjee, 2013. Synthesis of metallic nanoparticles using plant extracts. *Biotechnol Adv.*, 31(2): 346-56.
59. Sujitha, M.V. and S. Kannan, 2013. Green synthesis of gold nanoparticles using Citrus fruits Citrus limon, Citrus reticulata and Citrus sinensis aqueous extract and its characterization, *Spectrochim Acta A Mol. Biomol Spectrosc.*, 102: 15-23.
60. Tamuly, C., M.M. Hazarika, SCh Borah, M.R. Das and M.P. Boruah, 2013. In situ biosynthesis of Ag, Au and bimetallic nanoparticles using *Piper pedicellatum* C.D.C., green chemistry approach. *Colloids Surf B Biointerfaces.* 1(102):627-34.
61. Kumar, K.M., B.K. Mandal, M. Sinha and V. Krishnakumar, 2012. Terminalia chebula mediated green and rapid synthesis of gold nanoparticles. *Spectrochim Acta A Mol Biomol Spectrosc.*, 86: 490-4.
62. Elavazhagan, T. and K.D. Arunachalam, 2011. *Int J Nanomedicine.*, 6: 1265-78.
63. Das, R.K., N. Gogoi and U. Bora, 2011. Green synthesis of gold nanoparticles using *Nyctanthes arbortristis* flower extract. *Bioprocess Biosyst Eng.*, 34(5): 615-9.
64. Philip, D., C. Unni, S.A. Aromal and V.K. Vidhu, 2011. *Murraya Koenigii* leaf-assisted rapid green synthesis of silver and gold nanoparticles. *Spectrochim Acta A Mol Biomol Spectrosc.*, 78(2): 899-904.
65. Philip, D., 2010. Rapid green synthesis of spherical gold nanoparticles using *Mangifera indica* leaf. *Spectrochim Acta A Mol Biomol Spectrosc.*, 77(4): 807-10.
66. Bankar, A., B. Joshi, A.R. Kumar and S. Zinjarde, 2010. *Colloids Surf B Biointerfaces.*, 1.80(1): 45-50.
67. Smitha, S.L., D. Philip and K.G. Gopchandran, 2009. Green synthesis of gold nanoparticles using *Cinnamomum zeylanicum* leaf broth, *Spectrochim Acta. A Mol. Biomol Spectrosc.*, 15,74(3): 735-9.
68. Vinod, V.T., P. Saravanan, B. Sreedhar, D.K. Devi and R.B. Sashidhar, 2011. A facile synthesis and characterization of Ag, Au and Pt nanoparticles using a natural hydrocolloid gum kondagogu *Cochlospermum gossypium*. *Colloids Surf B Biointerfaces.*, 1, 83(2): 291-8.
69. Annamalai, A., V.L. Christina, D. Sudha, M. Kalpana and P.T. Lakshmi, 2013. Green synthesis, characterization and antimicrobial activity of Au NPs using *Euphorbia hirta* L. leaf extract. *Colloids Surf B Biointerfaces.*, 1(108): 60-65.
70. Tiwari, P.M., K. Vig, V.A. Dennis and S.R. Singh, 2011. Functionalized gold nanoparticles and their biomedical applications. *Nanomaterials*, 1: 31-63.
71. Dykman, L.A., V.A. Bogatyrev, S.Y. Shchyogolev and N.G. Khlebtsov, 2008. Gold Nanoparticles, Synthesis, Properties. Biomedical Applications *Izdatel'stvo Nauka, Moscow, in Russian.*
72. Guo, R., Y. Song, G. Wang and R.W. Murray, 2005. Does core size matter in the kinetics of ligand exchanges of monolayer-protected Au clusters? *Journal of American Chemical Society.*, 127: 2752-2757.

73. Chandran, S.P., M. Chaudhary, R. Pasricha, A. Ahmad and M. Sastry, 2006. Synthesis of gold nanotriangles and silver nanoparticles using Aloe vera plant extract. *Biotechnol Prog.*, 22(2): 577-83.
74. Sougata, Ghosh, Sumersing Patil, Mehul Ahire, Rohini Kitture, Deepanjali, D. Gurav, Amit, M. Jabgunde, Sangeeta Kale, Karishma Pardesi, Vaishali Shinde, Jayesh Bellare, Dilip, D. Dhavale and Balu, A. Chopade, 2012. Gnidia glauca flower extract mediated synthesis of gold nanoparticles and Evaluation of its Chemocatalytic Potential. *Journal of Nanobiotechnology.*, 10: 17.
75. Mubarak, Ali, D., N. Thajuddin, K. Jeganathan and M. Gunasekaran, XXXX. Plant extract mediated synthesis of silver and gold nanoparticles and its antibacterial activity against clinically isolated pathogens. *Colloids and Surfaces B, Biointerfaces*, 85(2): 360-365.
76. Sun, R.W., R. Chen, N.P. Chung, C.M. Ho, C.L. Lin and C.M. Che, 2005. *Chem Commun.*, 40: 5059-5061.
77. Krishnamurthy, N.B., B. Nagaraj, Barasa malakar, P. Liny and R. Dinesh, 2012. Green synthesis of gold nanoparticles using Tagetes erecta L., Mari gold flower extract and evaluation of their antimicrobial activities. *IJPBS.*, 3(1): 212- 221.
78. Stobie, N., B. Duffy, McCormack, J. Colreavy, M. Hidalgo and P. McHale, 2008. Prevention of Staphylococcusepidermidis biofilm formation using a low -temperatureprocessed silver doped phenyltriethoxysilane solgel coating. *Biomater.*, 29: 963-969.
79. Liny, P., T.K. Divya, Barasa malakar, B. Nagaraj, N. Krishnamurthy and R. Dinesh, 2012. Preparation of gold nanoparticles from Helianthus annuus Sunflower flowers and evaluation of their antimicrobial activities. *Ijpbs.*, 3(1): 439-446.
80. Sontara, Konwar Boruah, Prabin Kumar Boruah, Pradyut Sarma, Chitrani Medhi and Okhil Kumar Medhi, 2012. Green synthesis of gold nanoparticles using camellia sinensis and kinetics of the reaction. *Adv. Mat. Lett.*, 3(6): 481-486.
81. Yinghua, Qu. and Xiaoying Lü, 2009. Aqueous synthesis of gold nanoparticles and their cytotoxicity in human dermal fibroblasts-fetal, *Biomedical Materials*, 4: 2.
82. Asha Rani, P.V., Grace Low Kah Mun, Manoor Prakash Hande and Suresh Valiyaveetil, 2009. Cytotoxicity and Genotoxicity of Silver Nanoparticles in Human Cells, 3(2): 279-290.
83. Kim, H.S., S.H. Jun, Y.K. Koo, S. Cho and Y. Park, 2013. Green synthesis and nanotopography of heparin-reduced gold nanoparticles with enhanced anticoagulant activity, *J. Nanosci Nanotechnol.*, 13(3): 2068-76.
84. Bhat, R., V.G. Sharanabasava, R. Deshpande, U. Shetti, G. Sanjeev and A. Venkataraman, 2013. Photo-bio-synthesis of irregular shaped functionalized gold nanoparticles using edible mushroom Pleurotus florida and its anticancer evaluation. *J. Photochem Photobiol B.*, 5(125): 63-9.
85. Mukherjee, S., V. Sushma, S. Patra, A.K. Barui, M.P. Bhadra, B. Sreedhar and C.R. Patra, 2012. Green chemistry approach for the synthesis and stabilization of biocompatible gold nanoparticles and their potential applications in cancer therapy, *Nanotechnology*, 16,23(45): 455103.
86. Sreekanth, T.V.M., Nagajyothi, P.C. Lee and Kap Duk, 2012. Biosynthesis of Gold Nanoparticles and Their Antimicrobial Activity and Cytotoxicity. *Advanced Science Letters.*, 6(7): 63-69.
87. Armendariz, V., I. Herrera, J.R. Peralta-Videa, M. Jose Yacaman, H. Troiani, P. Santiago and J.L. Gardea- Torresdey, 2004. Size controlled gold nanoparticle formation by Avena sativa biomass: use of plants in nanobiotechnology. *J. Nanopart Res.*, 6: 377-82.
88. Muralidharan, G., L. Subramanian, S.K. Nallamuthu, V. Santhanam and Sanjeev Kumar, 2011. Effect of reagent addition rate and temperature on synthesis of gold nanoparticles in microemulsion route. *Ind. Eng. Chem. Res.*, 50: 8786-8791.
89. Mohamad, M.F., K.S.N. Kamarudin, N. Fathilah, N.F.N.M. and M.M. Salleh, 2011. The Effects of Sodium Chloride in the Formation of Size and Shape of Gold, Au Nanoparticles by microwave-polyol method for mercury adsorption. *World Acad. Sci. Eng. Technol.*, 74: 691-695.
90. Banoee1, M., N. Mokhtari1, A. Akhavan Sepahi, P. Jafari Fesharaki1, H.R. Monsef-Esfahani, Z. Ehsanfar1, M.R. Khoshayand and A.R. Shahverdi1, 2010. The green synthesis of gold nanoparticles using the ethanol extract of black tea and its tannin free fraction. *Iranian Journal of Materials Science & Engineering.*, 7(1): 48-53.
91. Edhaya naveena, B. and S. Prakash, 2013. Biological synthesis of gold nanoparticles using marine algae Gracilaria corticata and its application as a potent antimicrobial and antioxidant agent, *Asian J. Pharm Clin Res.*, 6(2): 179-182.



92. Akl M. Awwad, Nidá M. Salem and Amanya O. Abdeen, 2013. Green synthesis of silver nanoparticles using carob leaf extract and its antibacterial activity. *International Journal of Industrial Chemistry.*, 4: 29.
93. Sena, P.M. and X. Gao, 2010. Designing multifunctional quantum dots for bioimaging, detection and drug delivery. *Chem. Soc. Rev.*, 39: 4326-4354.
94. Lee, J.H., Y.M. Huh, Y. Jun *et al*, 2006. Artificially engineered magnetic nanoparticles for ultra-sensitive molecular imaging. *Nature Med.*, 13: 95-99.
95. Thomas, C.R., D.P. Ferris, J.H. Lee *et al*, 2010. Noninvasive remote-controlled release of drug molecules *in vitro* using magnetic actuation of mechanized nanoparticles. *J. Am. Chem. Soc.*, 132: 10623-10625.
96. Neuberger, T., B. Schopf, H. Hofmann, M. Hofmann and B. Von Rechenberg, 2005. Superparamagnetic nanoparticles for biomedical applications: possibilities and limitations of a new drug delivery system. *J. Magn. Magn. Mater.*, 293: 483-496.
97. Qian, X.M., X.H. Peng, D.O. Ansari *et al*, 2008. In vivotumor targeting and spectroscopic detection with surface-enhanced Raman nanoparticle tags. *Nat. Biotech.*, 26: 83-90.
98. Bai, X., S.J. Son, S.X. Zhang, *et al*. 2008. Synthesis of superparamagnetic nanotubes as MRI contrast agents and for cell labeling. *Nanomedicine.*, 3: 163-174.
99. Son, S.J., X. Bai, A. Nan, H. Ghandehari and S.B. Lee, 2006. Template synthesis of multifunctional nanotubes for controlled release, *J. Control. Release.*, 114: 143-152.
100. Son, S.J., J. Reichel, B. He, M. Schuchman and S.B. Lee, 2005. Magnetic nanotubes for magnetic-field-assisted bioseparation, biointeraction and drug delivery. *J. Am. Chem. Soc.*, 127: 7316-7317.
101. Mitchell, D.T., S.B. Lee, L. Troifin *et al*, 2002. Smart nanotubes for bioseparations and biocatalysis. *J. Am. Chem. Soc.*, 124: 11864-11865.
102. He, B., S.K. Kim, S.J. Son and S.B. Lee, 2010. Shape-coded silica nanotubes for multiplexed bioassay rapid and reliable magnetic decoding protocols. *Nanomedicine.*, 5: 77-88.
103. Son, S.J., X. Bai and S.B. Lee, 2007. Inorganic hollow nanoparticles and nanotubes in nanomedicine Part 1. Drug/gene delivery applications. *Drug Discov. Today.*, 12: 650-656.