

Screening of Polyethylene Degrading Microorganisms from Garbage Soil

R. Usha, T. Sangeetha and M. Palaniswamy

Department of Microbiology, School of Life Sciences,
Karpagam University, Coimbatore, 641 021, Tamil Nadu, India

Abstract: Plastic and polythene waste accumulating in the environment are posing an ever increasing ecological threat. Biodegradable plastics are environment friendly, they have an expanding range of potential application and are driven by the growing use of plastics in packaging. In this study, biodegradation of polythene bag and plastic cup were analyzed 2, 4 and 6 month of incubation in liquid culture method. The heterotrophic population of microbes in polythene and plastics, bacterial counts was recorded up to 62.71×10^4 and 56.52×10^4 , the fungal count ranged from 44.32×10^2 and 35.62×10^2 and actinomycetes count ranges from 72.54×10^4 and 64.75×10^4 . The microbial species associated with the polythene materials were identified as *Pseudomonas* sp, *Bacillus* sp, *Staphylococcus* sp, *Aspergillus nidulans*, *Aspergillus flavus* and *Streptomyces* sp. Efficacy of the microbes in degradation of polythene and plastics were analyzed in liquid (shaker) culture method, among the bacteria *Pseudomonas* sp degrade 37.09% of polythene and 28.42% of plastics in 6 month period. Among the fungal species 20.96% of polythene and 16.84% of plastics and *Streptomyces* species 46.16% of polythene and 35.78% of plastics. This work reveals that the *Streptomyces* sps possess greater potential to degrade polythene and plastics when compare with other bacteria and fungi.

Key words: Biodegradation % Garbage soil % Polythene % Plastics % *Streptomyces* sp

INTRODUCTION

Low density polyethylene is one of the major sources of environmental pollution. Polyethylene is a polymer made of long chain monomers of ethylene. The worldwide utility of polyethylene is expanding at a rate of 12% per annum and approximately 140 million tones of synthetic polymers are produced worldwide each year [1]. With such huge amount of polyethylene getting accumulated in the environment, their disposal evokes a big ecological issue. It takes thousand years for their efficient degradation.

Biodegradable polymers are designed to degrade upon disposal by the action of living organisms. Biodegradable polymers generally decompose in various medium in our environment. The depolymerisation results due to various physical and biological forces. The physical forces such as temperature, moisture, pressure etc, deal with causing mechanical damage to the polymer. The microbial biodegradation is widely accepted and is still underway for its enhanced efficiency. Recently several microorganisms have been reported to produce polyester degrading enzymes. The microbial species are associated

with the degrading materials were identified as bacteria (*Pseudomonas*, *Streptococcus*, *Staphylococcus*, *Micrococcus* and *Moraxella*), fungi (*Aspergillus niger*, *Aspergillus glaucus*), *Actinomycetes* sp. and *Saccharomonospora* genus [2].

Microbial degradation of plastics is caused by certain enzymatic activities that lead to a chain cleavage of the polymer into oligomers and monomers. These water soluble enzymatically cleaved products are further absorbed by the microbial cells where they are metabolized. Aerobic metabolism results in carbon dioxide and water [3], whereas anaerobic metabolism results in carbon dioxide, water and methane as the end products, respectively [4]. The degradation leads to breaking down of polymers to monomers creating an ease of accumulation by the microbial cells for further degradation.

The purpose of the present study was to isolate microorganism from garbage waste soil and screening of the potential polyethylene degrading microorganisms and identifying the high potential microorganism that degrade the polythene and plastics. A further objective was to determine the weight loss of polythene and plastic under liquid culture.

MATERIALS AND METHODS

Material: Low density polyethylene powder (LDPE) was obtained from Sigma Aldrich Chemical Co. (Germany).

Sample Collection: Garbage soil samples (waste disposable site dumped with polythene bag and plastic cup) were collected from sidco, coimbatore, Tamil nadu. The soil samples were collected at a depth of 3-5cm, in a sterile container and then air dried at room temperature.

Isolation of Polyethylene Degrading Microorganisms:

One gram of soil sample was transferred into a conical flask containing 99ml of sterile distilled water. This content was shaken and serially diluted. To isolate microorganisms associated with materials (polythene bag and plastic cup) by pour plate method was adopted using the starch casein agar for actinomycetes, nutrient agar for bacteria and sabouraud dextrose agar for fungi. For each dilution, three replicates were made. The plates were then incubated at 30°C for 2-7 days. The developed colonies were isolated and sub cultured repeatedly to get pure colonies and then preserved in slant at 4°C.

Screening of Polyethylene Degrading Microorganisms by Clear Zone Method [5]:

Polyethylene powder was added in mineral salt medium at a final concentration of 0.1% (w/v) respectively and the mixture was sonicated for 1hour at 120 rpm in shaker. After sonication the medium was sterilized at 121°C and pressure for 15 lbs/inch² for 20 minutes. About 15 ml sterilized medium was poured before cooling in each plate. The isolated organisms were inoculated on polymer containing agar plates and then incubated at 25-30°C for 2-4 weeks. The organisms, producing zone of clearance around their colonies were selected for further analysis.

Identification Polyethylene Degrading Microorganisms:

The identification of bacteria was performed on the basis of macroscopic and microscopic examination and biochemical test according to Bergey's manual of determinative bacteriology [6]. The fungus was identified after staining them with cotton blue by following the keys Raper and Fennell [7]. The phenotypic and chemotaxonomic characteristics of the actinomycetes were determined by the method described by Shirling and Gottlieb [8].

Microbial Degradation of Polythene and Plastics under Laboratory Conditions

Liquid Culture Method [9]: The pre weighted strip of 2cm diameter prepared from polythene bags and plastic cups

were aseptically transferred into the conical flask containing 100 ml of mineral salt medium and then inoculated with identified polythene degrading microorganisms. Control was maintained with polythene and plastic strips in the microbe free medium and left in a shaker at 30°C, 150 rpm for 2, 4 and 6 month period. After the period of shaking the strips were collected, washed thoroughly using distilled water, shade dried and then weighted to check the final weight. Finally the weight loss of the polythene bags and plastics were calculated and compared with control.

RESULTS AND DISCUSSION

Microorganisms Associated with Garbage Soil Samples:

The number of heterotrophic microbes was isolated from garbage soil sample and the bacterial population ranged from 62.71×10^4 polythene bag and 50.42×10^4 in the case of plastics. While the fungi count ranged from 36.24×10^2 polythene and 28.16×10^2 in case of plastics. The actinomycetes count ranged from 68.54×10^4 polythene and 56.22×10^4 in case of plastics. The total number of microbes associated with polythene and plastics showed some variation. Vijaya, reported that average number of heterotrophic bacteria and fungi found in association with polythene film and plastic cups were 37.08×10^4 and 38.04×10^4 , 26.94×10^2 and 35.13×10^2 respectively [10]. Kathiresan, (2001) reported that the plastic materials in mangrove soil have shown rich total heterotrophic bacterial counts of up to 79.67×10^4 and fungal counts of up to 55.33×10^2 and the plastic materials have been colonized commonly by five species of bacteria and two species of fungi [11]. Abundance of polymer degrading microorganisms in a seabed solid waste disposal site has been reported by Ishigaka *et al* [12]. Imam *et al* observed that significant biodegradation occurred only after colonization of the plastic, a parameter that was dependent on the resident microbial populations. Therefore, it can be reasonably inferred that an increase in the bacterial load has correlation with degradation of the polymer [13].

Screening and Identification of Polyethylene Degrading Microorganisms:

The polyethylene containing mineral salt agar plates were inoculated with the isolated bacteria, fungi and actinomycetes. All isolates were screened for their degradation activity. Clear zone was observed after 10 days of incubation at 25-30°C around the colony. On this screening 5 of *Streptomyces* sp, one of *Pseudomonas* sp, *Bacillus* and *Staphylococcus* sp two of *Aspergillus* sp showed high degradation activity. Similar type of

organisms were reported earlier which associated with the polythene bag and plastic films in the soil [14]. Further these soil microorganisms were reported to have the ability for degrading plastics. However the strains with high degradation activity were selected for fermentation.

Augusta *et al.*, reported that the extracellular hydrolyzing enzymes secreted by the target organism hydrolyze the suspended polyesters in the turbid agar medium into water soluble products thereby producing zones of clearance around the colony [15]. Kambe *et al.* isolated and characterized a bacterium from soil which utilizes polyester polyurethane as a sole carbon and nitrogen source. Two strains with good polyurethane degrading activity were isolated and identified as *Comamonas acidovorans* [16]. Oda *et al.* [17] studied the Polycaprolactone depolymerase produced by the bacterium *Alcaligenes faecalis*. He isolated several bacteria capable of degrading polycaprolactone (PCL) from soil and activated sludge.

Webb *et al.* [18] studied the fungal colonization and biodeterioration of plasticized polyvinyl chloride *in situ* an *ex situ* conditions. These results suggest that microbial succession may occur during the long periods of exposure in *in situ*. They have identified *Aureobasidium pullulans* was the principal colonizing fungus and a group of yeasts and yeast-like fungi, including *Rhodotorula aurantiaca* and *Kluyveromyces* spp. Incidence of marine and mangrove bacteria accumulating polyhydroxy alkanooates on the mid-west coast of India has been reported by Rawte *et al.* [19].

Microbial Degradation of Polythene and Plastics in Laboratory Condition

Determination of Weight Loss: Selected microorganisms were further tested in the laboratory condition to check the ability of degrading polythene and plastics. The bacteria, fungi and actinomycetes separately allowed to degrade the polythene and plastic under shaking condition for period of 2, 4 and 6 months. After the period of shaking the strips were collected, washed thoroughly using distilled water, shade dried and then weighted to check the final weight (Table1). These microorganisms utilize polythene film as a sole source of carbon resulting in partial degradation of plastics. They colonize on the surface of the polyethylene films or plastic cups forming a biofilm. Cell surface hydrophobicity of these organisms was found to be an important factor in the formation of biofilm on the polythene surface, which consequently enhanced biodegradation of the polymers.

Kathiresan and Bingham, [11] reported that bacteria caused the biodegradation ranging from 2.19 to 20.54% for polythene and 0.56 to 8.16% for plastics. Among all the species, *Aspergillus glaucus* was more active than *A. niger* in degrading 28.8% of polythene and 7.26% of plastics within a month. This may be attributed to the thickness of the polythene that is 5-times thinner than the plastics.

Once the organisms get attached to the surface, it starts growing by using the polymer as the carbon source. In the primary degradation, the main chain cleaves leading to the formation of low-molecular weight fragments (oligomers), dimers or monomers [20]. The degradation is

Table 1: Comparative analysis of polythene and plastics weight loss with different microbial species in shaker cultures under laboratory conditions

Name of microbes	Microbial degradation (% weight loss)					
	2 nd month		4 th month		6 th month	
	Polythene	Plastics	Polythene	Plastics	Polythene	Plastics
Actinomycetes						
<i>Streptomyces</i> KU8	22.58±0.03	10.52±0.31	35.48±1.01	21.05±0.23	46.16±0.01	35.78±0.20
<i>Streptomyces</i> KU5	9.67±0.02	6.31±0.18	16.12±0.20	11.57±0.14	22.58±0.16	17.89±0.12
<i>Streptomyces</i> KU1	6.45±0.41	4.21±0.06	19.35±0.02	9.47±0.05	25.80±0.01	24.21±0.03
<i>Streptomyces</i> KU6	9.67±0.02	3.15±0.10	17.74±0.09	10.86±0.08	30.64±0.05	20.00±0.05
Bacteria						
<i>Pseudomonas</i> sp	9.67±0.14	6.45±0.16	25.80±0.02	20.00±0.10	37.09±0.01	28.42±0.11
<i>Bacillus</i> sp	4.22±0.31	3.15±0.10	11.29±0.10	10.5±0.05	30.64±0.08	24.21±0.02
<i>Staphylococcus</i> sp	3.61±0.01	2.21±0.12	6.31±0.08	4.83±0.08	17.89±0.06	16.12±0.11
Fungi						
<i>A.nidulans</i>	4.21±0.10	3.22±0.02	6.45±0.27	8.42±0.06	12.63±0.05	11.29±0.05
<i>A.flavus</i>	8.06±0.14	7.36±0.20	16.12±0.05	11.57±0.19	20.96±0.15	16.84±0.12

due to the extra cellular enzyme secreted by the organism. These low molecular weight compounds are further utilized by the microbes as carbon and energy sources. The resultant breakdown fragments must be completely used by the microorganisms, otherwise there is the potential for environmental and health consequences [21].

Actinomycetes are the most widely distributed group of microorganisms in nature which primarily inhabit the soil [22]. Many of them are known to have the capacity to degrade plastic materials and synthesis bioactive secondary metabolites which include enzymes, herbicides, pesticides and antibiotics.

CONCLUSION

The isolated microbes were native to the site of polyethylene disposal and might show some degradability in natural conditions, yet they also exhibited biodegradation in laboratory conditions on synthetic media. This gives some suggestion that these microbes can be used in both natural and artificial conditions for the purpose of degradation of polymers. Our knowledge, microbes cause greatest degradation of polythene and plastics. Among the microbes, viz *Streptomyces* sp, *A. nidulance* and *Pseudomonas* sp, the *Streptomyces* sp having greater degradation ability when compared with fungi and other bacteria. Hence, the further attention is required from microbiologists for commercial degradation and eco-friendly polyethylene with *Streptomyces* sp.

REFERENCES

1. Shimao, M., 2001. biodegradation of plastics. Curr. Opin. Biotechnol., 12: 242-247.
2. Swift, G., 1997. Non-medical biodegradable polymers: environmentally degradable polymers. Handbook of biodegradable polymers. Hardwood Academic, Amsterdam. pp: 473-511.
3. Starnecker, A. and M. Menner, 1996. Assessment of biodegradability of plastics under stimulated composting conditions in a laboratory test system. International biodeterioration and Biodegradation, pp: 85-92.
4. Gu, J.D., T.E. Ford, D.B. Mitton and R. Mitchell, 2000. Microbial corrosion of metals. The uhling corrosion hand book. 2nd Edition. Wiley, New York, USA, pp: 915-927.
5. Augusta, J., R.J. Muller and H. Widdecke, 1993. A rapid evaluation plate-test for the biodegradability of plastics. Appl. Microbiol. Biotechnol., 39: 673-678.
6. Holt, J.G., N.R. Krieg, P.H.A. Sneath, J.T. Staley and S.T. Williams, 1994. Gram-Positive Cocci. In: Bergey's Manual of Determinative Microbiology, Hensyl, W.R. (Ed.). 9th Edn., Williams and Wilkins, Baltimore, USA., pp: 527-558.
7. Raper, K.B. and D.I. Fennell, 1987. The genus *Aspergillus*. R.E. Krieger(ed). Huntington, New York, pp: 686.
8. Shirling, E.B. and D. Gottlieb, 1966. Methods for characterization of *Streptomyces* species. Int. J. Syst. Bacteriol., 16: 313-340.
9. Orhan, Y., J. Hrenovic and H. Buyukgungor, 2004. Biodegradation of plastic compost bags under controlled soil conditions. Acta Chim. Slov. 51: 579-588.
10. Ch Vijaya. and R. Mallikarjuna Reddy, 2008. Impact of soil composting using municipal solid waste on biodegradation of plastics. Indian J. Biotechnol., 7: 235-239.
11. Kathiresan, K. and B.L. Bingham, 2001. Biology of mangroves and mangrove ecosystems. Advances Mar. Biol., 40: 81-251.
12. Ishigaka, T., W. Sugano, M. Ike, Y. Kawagoshi and M. Fujita, 2000. Abundance of polymers degrading microorganisms in sea based solid waste disposal site. J. Basic Microbiol., 40: 177-186.
13. Imam, S.H., S.H. Gordon, R.L. Shogren, T.R. Tosteson, N.S. Govind and R.V. Greene, 1999. Degradation of starch- poly (b-Hydroxybutyrate-Co-b- Hydroxyvalerate) bioplastic in tropical coastal waters. Appl. Environ. Microbiol., 65: 431-437.
14. Kathiresan, K., 2003. Polythene and plastics degrading microbes form mangrove soil. Rev. Biol. Trop., 51: 629-634.
15. Augusta, J., Müller, R.J. and H. Widdecke, 1993. A rapid evaluation plate-test for the biodegradability of plastics. Appl. Microbiol. Biotechnol., 39: 673-678.
16. Nakajima-Kambe, T., F. Onuma, N. Kimpara, T. Nakahara, 1995. Isolation and chareacterization of a bacterium which utilizes polyester polyurethane as a sole carbon and nitrogen source. FEMS Microbiology Letters., 129: 39-42.
17. Oda, Y., N. Oida, T. Urakami and K. Tonomura, 1998. Polycaprolactone depolymerase produced by the bacterium *Alcaligenes faecalis*. FEMS Micobiol. Lett., 150: 339-343.
18. Webb, J.S., M. Nixon, I.M. Eastwood, M. Greenhalgh, G.D. Robson and P.S. Handley, 2000. Fungal colonization and biodeterioration of plasticized polyvinyl chloride Appl. Environ. Microbiol., 66: 3194 -3200.

19. Rawte, T., M. Padte and S. Mavinkurve, 2002. Incidence of marine and mangrove bacteria accumulating polyhydroxyalkanoates on the mid-west coast of India. *World J. Microbiol.*, 18: 655-659.
20. Vasile, C., 1993. Degradation and decomposition, in *Handbook of polyolefins synthesis and properties*, edited by C Vasile and R B Seymour (Marcel Dekker Inc, New York)., pp: 479-509.
21. Narayan, R., 2006. Biobased and biodegradable polymer materials: rationale, drivers and technology exemplars. *American Chemical Society Symposium Ser.*, 939(18): 282.
22. Oskay, M., A.U. Tamer and C. Azeri, 2004. *African J. Biotechnol.*, 3(9): 441- 446.